## PATENT ABSTRACTS OF JAPAN

(11)Publication number:

58-189104

(43) Date of publication of application: 04.11.1983

(51)Int.Cl.

A01N 59/08

A01N 59/00

A01N 59/14

A01N 59/26

//(A01N 59/08

A01N 59/14

A01N 59/26

A01N 59/00

A01N 33/12

A01N 43/40 )

(21)Application number: 57-072961

(71)Applicant: KAO CORP

(22)Date of filing:

30.04.1982

(72)Inventor: NAKAI RYOZO

**INOUE SHIGEO** 

**ARAI SUMIO** 

## (54) WOOD-PRESERVING COMPOSITION

(57)Abstract:

PURPOSE: A wood-preserving composition that contains an alkyl ammonium as an active ingredient and a specific strong alkaline substance as an assistant, thus showing improved sticking tendency of the active ingredients.

CONSTITUTION: The objective wood-preserving composition is prepared by dissolving at least one selected from strong alkaline substance such as alkali hydroxides, alkali orthoborates, alkali metaborates, alkali perborates, alkali orthophosphate, alkali orthosilicate and alkali metasilicate such as sodium hydroxide in at least one of alkyl ammnoiums, preferably of formula I or II (R1 is alkyl, alkenyl; R2, R3 are alkyl, hydroxyalkyl, aralkyl; R4 is alkyl; R5 is alkyl; X is inorganic or organic acid

D

radical) such as lauryl dimethyl benzyl ammonium chloride.

## **LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]